

ALAC444501 Architectural Series
Acoustic Core STC 44/45-Minute-HPDL

Positive Pressure	5 Ply—Architectural-Grade Laminate .050 nominal
Thickness	1-3/4" Only
Maximum Sizes	45-Minute: Single $3^0 \times 7^0$ Pairs not available
Core	Proprietary non-combustible, asbestos free, NAF acoustic core
Edges	Stiles: GP Fire-stop. Per WH / ITS Testing Requirements. (1) Rails: GP Fire-stop. Per WH / ITS Testing Requirements. (2)
Edge Construction	Category A: Integral intumescent edge construction available Category B: Frame mounted intumescent edge construction standard
Faces	Decorative Laminate – AWI-HPDL, NEMA-LD-3 .05 nominal thickness applied over NAF High Density Fiberboard (HDF).
Adhesive	Type 1—Waterproof Bond NAF
Core Bonding	Stiles and rails are securely bonded utilizing type 1 adhesive in conjunction with superior RF bonding technology. To ensure freedom from telegraphing of core components, the core unit is then sanded before face veneers are applied.
Warranty (3)	Interior Use—Life of installation Exterior Use—No Warranty
Construction Standards	Meet or ExceedWDMA I.S. 1-ANFPA 80AWS Section 9WH/ITS Labeling ServiceUBC7-2-1997UL10CASTM E 90 under Architectural Testing Inc.
Performance Standards	Meets or exceeds WDMA I.S.1-A Heavy Duty performance
Factory Machining	> Pre-fitting >Templated hardware prep > Lite cutouts (consult factory) Consult factory for full list of machining options
Gasketing	Gasket system #101, supplied by others, required for approved STC rating. Contact factory for hardware details and test report
Sustainability	CALGreen Compliant GREENGUARD and GREENGUARD Gold Certified No-Added Formaldehyde (NAF) Extracted: Clarksville, Iowa. Manufactured: Winston, Oregon



⁽²⁾ Wider rails and internal blocking are available for hardware reinforcement.

(3) See complete Oregon Door Warranty for details.



